TECH-MASTERS Trading GmbH Perfektastraße 55, A-1230 Wien Tel: +43 (0)1 / 867 29 07 office@tech-masters.com www.tech-masters.eu



SEF-B

THE LIQUID GASKET

- · The ideal gasket without molds
- Workable in few minutes
- Created for automotive applications
- It fills the unevenness
- Non corrosive
- · Immediate results on water or air
- High chemical resistance; it resists also against engine oil
- High pressure and UV resistance
- Temperature range: -60°C to + 270°C, temporary up to 300°C
- · Easy to remove



SEAL FLEX HT BLACK/GREY

General Information

SEAL FLEX HT BLACK/GREY is a modified, uv-resistant sealant, based on acetoxy RTV silicone, that is essentially odorless. This non-corrosive silicone, with excellent adhesive properties, can be used on a wide variety of materials and especially where no discoloration or corrosion of sensitive materials is accepted.

Technical Information

Form: pasty Material: acetoxy RTV silicone Colour: black or grey Odour: characteristic Density (at 20°C): 1,04 g/cm³ Viscosity: non-sag paste Tack-free time: 10 min Cure time (at 23°C, 50% r.h.): 4mm/24h Hardness Shore A: 25 Tensile strength: 1,8 MPa Shear strength (alu, 1mm): 2,0 MPa Elastic Modulus (100%): 0,52 MPa

Application and Use

- SEAL FLEX HT BLACK/GREY is developed for many industrial sealing and insulating application, including metal and glass construction, automotive, marine, mechanical engineering, screw thread connections, machine tools, maintenance, connections, air ducts, inlet and outlet manifolds, compressors, pumps, turbines, electrical/electronic, aerospace and consumer products.
- insulating and moisture-proofing of engine and electrical boxes
- sealing of water leakages on rear lights and body joints

SEAL FLEX HT BLACK/GREY forms a strong, tough, flexible and resilient elastomeric rubber, with excellent chemical and high temperature resistance, that maintains its flexibility at low temperatures and stability at high temperatures. Apply SEAL FLEX HT without using any extra tools

Apply SEAL FLEX HT without using any extra tools directly from the pressure can.

Elongation at break: 500% Recovery from deformation: 98% Temperature resistance: -60°C to 270°C, temporary until 300°C

Dielectric strength: 20 kv/mm (ASTM D 419) Dielectric constant: 3 at 1 Mhz (ASTM D 150) Dielectric dissipation factor: 3x10-3 at 1 Mhz (ASTM D 150)

Volume resistivity: 2x1015 OHM cm (ASTM D 257) Thermal conductivity: 315 cal/sec./cm², °C/cm Shelf life: 12 months in unopened packing below 25°C

- SEAL FLEX HT BLACK/GREY is jointing to: metals and different alloys, glass, ceramics and several kinds of synthetic materials
- SEAL FLEX HT BLACK/GREY is resistant to: light acids (up to 20%), glycol, fluor-chlorine-methane, butane, oils, greases, lubricants, petrol, kerosene, transmission and brake fluids, water, steam, antifreeze agents, fuel oil, alkali, saline solutions
- For an optimal adhesion, the surfaces should be dry and free from corrosion, oil/grease or dust. Therefore we recommend cleaning the surface with a solvent.
- We recommend to test SEAL FLEX HT on the substrate before use

Article nr	Name	Content	Section
T571101	Seal Flex HT black	200ml	ADHESIVES AND SEALANTS
T571301	Seal Flex HT grey	200ml	ADHESIVES AND SEALANTS



Notice

All information including images are given with the greatest care. Still, it is appropriate to users regardless of the test the suitability of each product for their own purposes. Tech-Masters is not liable for the completeness and accuracy of information and refuses warranty for your specific use. The guarantee, which Tech-Masters products provide, relates only to the standard conditions of sale of this product. In no case Tech-Masters can be held responsible for incidental damages, or damages for improper use or sale of the product to another customer.



ADHESIVES AND SEALANTS WWW.TECH-MASTERS.EU