TECH-MASTERS Trading GmbH Perfektastraße 55, A-1230 Wien Tel: +43 [0]1 / 867 29 07 office@tech-masters.com www.tech-masters.eu



### **Automotive**

## **TFT2U**

## TRANSPARENT ULTRA HIGH SOLID

- · 65% solid content.
- Antistatic effect, reduces painting defects.
- High brilliance.
- Easy to polish.
- · It reduces painting costs.
- It increases the productivity.

# **TECHNO FINISHER 2K UHS**

#### **GENERAL INFORMATION**

TECHNO FINISHER 2K UHS is a transparent ultra high solid with high brilliance. Thanks to its antistatic effect, it repels dust during painting process, reducing painting defects.

TECHNO FINISHER 2K UHS is a new technology that guarantees an easy application and a perfect final result. It is an easy

product that reduces polishing time; it contains a high solid contents; it is possible to obtain a perfect result, even with only one coat, so it reduces working time and painting costs. TECHNO FINISHER 2K UHS is compatible with water based and solvent based products.

#### **TECHNICAL INFORMATION**

Type: Hydroxylated acrylic resin. Solid Content: 65% Colour: transparent. VOC: 2004/42/CE IIB: (d-420 g/L max) cont. 418 g/L. Specific weight:  $1010 \pm 20 \text{ g}$  / l. Mixing ratio: 2:1. Pot-life  $(20^{\circ}\text{C})$ : 5-6 h.

Spraying viscosity: 20±2" Coppa Ford Ø 4 a 20°C.

Gravity feed spray gun: Ø 1,2 - 1,4 mm. Air pressure (Bar): 3-3,5 ATM.

Number of coats: 1 full coat or 1 light coat + 1 coat.

Dry film thickness: 60 microns. Flash time: 8-10 min. Dust free (20°C): 20-25 min. Touch Dry (20°C): 6-7 h. Drying time: 60°C 30 min.

#### **APPLICATION AND USE**

- TECHNO FINISHER 2K UHS guarantees a perfect coverage and a high glossy effect, even with only one coat.
- TECHNO FINISHER 2K UHS has a high filling effect; it makes easy the application on vertical panels, avoiding drips.
- TECHNO FINISHER 2K UHS product doesn't chap, yellow or exfoliate. It resists to weather conditions and UV rays.
- Mixing ratio with hardener: 2:1.
- Use Fast Hardener at temperature between +5°C and +15°C
- Use Medium Hardener at temperature between  $+15\,^{\circ}\text{C}$  and  $25/30\,^{\circ}\text{C}$
- Use Slow Hardener at temperatures higher than +25/30°C

Article nr	Name	Content	Section
T122003	Techno Finisher 2K UHS	51	SURFACE PROTECTION AND
			TREATMENT
T122013	Techno Finisher 2K UHS Hardener	2,51	SURFACE PROTECTION AND
	Medium		TREATMENT
T122023	Techno Finisher 2K UHS Hardener Slow	2,51	SURFACE PROTECTION AND
			TREATMENT
T122033	Techno Finisher 2K UHS Hardener Fast	2,51	SURFACE PROTECTION AND
			TREATMENT

#### **NOTICE**

All information including images are given with the greatest care. Still, it is appropriate to users regardless of the test the suitability of each product for their own purposes. Tech-Masters is not liable for the completeness and accuracy of information and refuses warranty for your specific use. The guarantee, which Tech-Masters products provide, relates only to the standard conditions of sale of this product. In no case Tech-Masters can be held responsible for incidental damages, or damages for improper use or sale of the product to another customer.



