TECH-MASTERS Trading GmbH Perfektastraße 55. A-1230 Wien Tel: +43 (0)1 / 867 29 07 office@tech-masters.com www.tech-masters.eu

SET-A

ALUCOLOURED MS POLYMER

- Special colour for metal surfaces
- Can be applied on wet and dry surface Durably elastic
- High absorption of acoustic vibrations
- Fast-curing, 3mm per 24 hours
- No shrinkage
- High mechanical resistance
- Mould and bacteria resistant
- No edging contamination with marble and natural stone
- Isocyanate-, solvent- and silicone-free Can be painted over with most
- water-based and 2K paint systems



General Information

SEAL TECH ALU is a unique adhesive and construction joint sealant for bonding all types of materials that is aluminium coloured and adjusts slightly on the metal surface it is applied on. SEAL TECH ALU can

Technical Information

Base: Silan-terminated polymers Colour: Aluminium Curing method: Exposure to air humidity Non-slump properties: Non-slump; < 2mm Extrusion rate: > 100 g/min Specific weight: 1.1 g/cm3 Skinforming time: 15 minutes Curing rate: 3mm/24 hours Shrinkage: < 3% Tensile strength: 2.5 N/mm² Elongation at break: 500% Shore A Hardness: 45

Application and Use

Article nr

T569801

APPLICATION: For the adhesion of lead, zinc, copper, synthetics and cond stone. Can be used adhesives with its

be used on any substrate, is extremely versatile and the answer to any desired bonding. SEAL TECH ALU is completely free of solvents, plasticizers, silicones and isocyanates. SEAL TECH ALU dries quickly and remains elastic.

SEAL TECH ALU

Movement capability: 10% relative to the initial width of the joint Chemical resistance Good: water, seawater, aliphatic solvents, oils, greases, diluted organic acids, lyes Temperature resistance: -40°C to +100°C Application temperature: +5°C to +40°C (substrate temperature) Storeage temperature: +5°C to 25°C

ON: hesion of all metals, v copper, mirrors, ston- and concrete and typ be used to replace a with its versatility.	e, polystyrene, es of natural	residues with MEGA FC - Apply SEAL TECH ALL GUN/TMT CAULKING D side of the material to 20 cm apart. It is not r pads. - When bonding mirror the adhesive only in ve stagnant moisture due - Due to the wide varie and compositions, and stress cracking, prelim recommended. Test ac powder coatings, exoti materials. - Due to the variety of the market, we recomm - After application, give necessary support for - Use SAFE CLEAN for s removing uncured poly	d remove dirt and grease DAM or SAFE CLEAN. J with the TMT CAULKING RILL ADAPTOR on one be bonded in lines 10 to ecommended to use is in sanitary rooms, apply ertical lines to avoid to condensation. ety of different plastics for materials prone to inary tests are dhesion to plastics, ic woods and bituminous paints and coatings on mend preliminary tests. e the materials the 24 hours. safe cleaning and
Name	Content	Shelf Life	Catalog
Seal Tech Alu	310ml	see imprint + 12 months	ADHESIVES AND SEALANTS

Notice

All information including images are given with the greatest care. Still, it is appropriate to users regardless of the test the suitability of each product for their own purposes. Tech-Masters is not liable for the completeness and accuracy of information and refuses warranty for your specific use. The guarantee, which Tech-Masters products provide, relates only to the standard conditions of sale of this product. In no case Tech-Masters can be held responsible for incidental damages, or damages for improper use or sale of the product to another customer.





