TECH-MASTERS Trading GmbH Perfektastraße 55, A-1230 Wien Tel: +43 (0)1 / 867 29 07 office@tech-masters.com www.tech-masters.eu



# AFR

#### 100% SOLVENT-FREE GLUE REMOVER FOR CYANOACRYLATE GLUES

- 100% solvent-free.
- Dissolves fast and easily superfast adhesives.
- Removes hardened as well as non-hardened cyanoacrylate adhesives.
- Simplifies the removal of hardened PU-foam.

# **GENERAL INFORMATION**

AL-FIX REMOVER is a 100% active removing agent without solvent, for adhesives based on ethyl cyanoacrylate. AL-FIX REMOVER removes AL-FIX from various materials.

## TECHNICAL INFORMATION

Form: liquid Colour: colourless Odour: characteristic Flammability: combustible Dynamic viscosity (at 20°C): 1 mPas Kinematic viscosity (at 20°C): 1 mm²/s Melting point: -18°C Boiling point: 203°C Relative density: 1.1

### APPLICATION AND USE

depend on application.

- suitable for removing residual glue from: most metals, aluminium, glass, plexiglass, polyester, polystyrene, ceramics, ...
  Apply and allow the product to act; time will
  - Always check the material being treated for registrance and colourfactness on an
  - resistance and colourfastness on an inconspicuous area.

| Article nr | Name           | Content | Section                |
|------------|----------------|---------|------------------------|
| N501080    | Al-Fix Remover | 20ml    | ADHESIVES AND SEALANTS |



#### NOTICE

All information including images are given with the greatest care. Still, it is appropriate to users regardless of the test the suitability of each product for their own purposes. Novatio is not liable for the completeness and accuracy of information and refuses warranty for your specific use. The guarantee, which Novatio products provide, relates only to the standard conditions of sale of this product. In no case Novatio can be held responsible for incidental damages, or damages for improper use or sale of the product to another customer.





ADHESIVES AND SEALANTS WWW.TECH-MASTERS.EU



AL-FIX REMOVER can also be used as a softener for other glues and polyurethane foams.

Absolute density: 1061 kg/m<sup>3</sup> Viscosity MPa's Brookfield 20°C: 1 Specific gravity gr/mm<sup>3</sup>: 1,06 Flashpoint DIN 55213: 110°C Dissolving time at 20°C: 30 sec Without solvent Shelf life: 36 months, keep dry, cool and frost-proof Safety measures: consult the Safety Data Sheet

· Remove the adhesive residue.

Auto-ignition temperature: 460°C

