

Automotive TECHNO FINISHER 2K HS

GENERAL INFORMATION

TECHNO FINISHER 2K HS is a new generation 2-component, anti-scratch transparent, perfect for wide surfaces and for spot repairs. Usable on matt bases, metallizes with water or solvent. It contains additives that

TECHNICAL INFORMATION

Type: Hydroxylated acrylic resin. Solid dontent: 53% Colour: transparent. VOC: 2004/42/CE IIB. Ready to use: (c-840 g/L max) cont. 498 g/L. Specific weight: 1010 \pm 20 g / l. Mixing ratio: 2:1. Spraying viscosity: 15 \pm 5" Coppa Ford Ø 4 at 20°C Pot-life (20°C): 5-6 h. Gravity feed spray gun: Ø 1,3 - 1,4 mm. Suction feed spray gun: Ø 1,5 - 1,6 mm.

APPLICATION AND USE

- TECHNO FINISHER 2K HS is recommended for wide surfaces and spot repairs.
- TECHNO FINISHER 2K HS contains special additives that make easy the spray application, reducing working time.
- TECHNO FINISHER 2K HS is recommended a first light application (½ coat), wait for 6-8 minutes, then apply another layer to complete the covering.

make easy the spray application and improve the product détente; in this way, it reduces working time and costs. TECHNO FINISHER 2K HS guarantees high brilliance for long time.

Air pressure (Bar): 3 - 3,5 ATM Number of coats: ½+1 normal - wait time 6-8 min. Dry film thickness: 45-50 microns. Flash time: 6-8 min. Dust free (20°C): 15 min. Touch dry (20°C): 5-6 h. Ready to be assembled: 12-16 h. Drying time: 20°C 24 h, 60°C 30 min.

- Mixing ratio with hardener: 2:1.
- Use Fast Hardener at temperature between +5°C and +15°C
- Use Medium Hardener at temperature between +15°C and 25/30°C
- Use Slow Hardener at temperatures higher than +25/30°C

Article nr	Name	Content	Section
T122004	Techno Finisher 2K HS	51	SURFACE PROTECTION AND TREATMENT
T122014	Techno Finisher 2K HS Hardener Medium	2,51	SURFACE PROTECTION AND TREATMENT
T122024	Techno Finisher 2K HS Hardener Slow	2,51	SURFACE PROTECTION AND TREATMENT
T122034	Techno Finisher 2K HS Hardener Fast	2,51	SURFACE PROTECTION AND TREATMENT

NOTICE

All information including images are given with the greatest care. Still, it is appropriate to users regardless of the test the suitability of each product for their own purposes. Tech-Masters is not liable for the completeness and accuracy of information and refuses warranty for your specific use. The guarantee, which Tech-Masters products provide, relates only to the standard conditions of sale of this product. In no case Tech-Masters can be held responsible for incidental damages, or damages for improper use or sale of the product to another customer.





WWW.TECH-MASTERS.EU

Perfect finishing: as original equipment. Perfect on matt bases, metallized with water or solvent.

TFT2H

HIGH SOLID

· Easy to apply.

TRANSPARENT ACRYLIC

• High solid content (more than 50%).

• Fast curing and perfect detente.